

Technical Data Sheet

Intended use: Addition vulcanizing ear impression silicone

Manufacturer: Dreve Otoplastik GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	chemical term
1	vinyl containing polydimethylsiloxane
2	silicic acid
3	filling materials
4	pigments

Colour: green
(corresponds to released sample in the house)

Processing time: 100 sec ± 15 sec at 23 °C

Setting time: 3 min ± 15 sec at 37 °C

Final hardness: 35 ± 2 Shore A

Consistency: putty consistency - type 0
(according to DIN EN ISO 4823)

Recovery from deformation: > 99.6 % (according to DIN EN ISO 4823)

Strain in compression: 4.3 % ± 0.5 % (according to DIN EN ISO 4823)

Linear dimensional change: < 0.2 % (according to DIN EN ISO 4823)

Dreve Otoplastik GmbH

Max-Planck-Str. 31

59423 Unna / Germany

Tel.: 02303 / 8807-0

Fax: 02303 / 82909

info@dreve.de

www.dreve.com